

**TECHNICAL DATA SHEET****ACRYNAL 7203 - 60****I. DESCRIPTION**

ACRYNAL 7203 - 60 is an acrylic thermosetting resin designed to cross-link with melamine resin in baking systems.

II. PERFORMANCE

- Weathering resistance.
- High gloss.
- High hardness.
- Solvent resistance.

III. SUGGESTED USES

- Automotive baking enamels.
- Metallic top clear coat for automotive (wet on wet system).

IV. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 60 ± 1 %
- Viscosity (25 °C, Gardner-Holdt) : Z₃ - Z₅
- Acid value (mg KOH /g solid) : 8 - 11
- Color (Gardner-Holdt) : maximum 1
- Appearance : clean & clear
- Specific Gravity (25 °C) : ca. 1.028

V. STANDARD PACKING

210 kgs in metal drums.

VI. STORAGE AND HANDLING

- Store in proper warehouse.
- Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.