

**TECHNICAL DATA SHEET****EBA 1462 - 70 AA****I. DESCRIPTION**

EBA 1462 - 70 AA is a short oil alkyd resin based on mixed oil developed for the vehicle in finishes where fast dry & yellowing resistance is required

II. PERFORMANCE

- Fast dry.
- Good hardness & adhesion.
- Good yellowing resistance.
- Good film build & Good flexibility.

III. SUGGESTED USES

- PU for wood finishes.
- NC lacquer.
- Amino-alkyd acid curing.

IV. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 70 ± 1 %
- Viscosity at 25 °C, cPs : 25,000 - 50,000
(Brookfield LVT, No.4/12 rpm)
- Acid Value (mg KOH/g solid) : maximum 10
- Color (Gardner-Holdt) : maximum 2
- Appearance : clean & clear
- Specific Gravity (25 °C) : ca. 1.076
- OH Value (mg KOH/g solid) : ca. 120

V. STANDARD PACKING

210 kgs in metal drums.

VI. STORAGE AND HANDLING

- Store in proper warehouse.
- Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.