



TECHNICAL DATA SHEET

EBA 1551 - 60

I. DESCRIPTION

EBA 1551 - 60 is a polyurethane modified alkyd designed for air-drying system applications with superior in drying time, excellent hardness and abrasion resistance. To improve the drying time & hardness of long oil alkyd, it can be blended with long oil alkyd at 30% of polyurethane modified alkyd based on solid weight of resins for synthetic paint.

II. PERFORMANCE

- Fast dry.
- Excellent hardness.
- Excellent abrasion.
- High gloss.

III. SUGGESTED USES

- Wood varnishes.
- Marine paint.
- Heavy duty coatings.

IV. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 60 ± 2 %
- Viscosity (25 °C, Gardner-Holdt) : Z2 - Z4
- Acid Value (mg KOH/g solid) : maximum 5
- Color (Gardner-Holdt) : maximum 6
- Appearance : clear & clean

V. STANDARD PACKING

200 kgs in metal drums.

VI. STORAGE AND HANDLING

- Store in proper warehouse.
- Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.