

TECHNICAL DATA SHEET

EBP - 2318

I. <u>DESCRIPTION</u>

EBP - 2318 is an air dry, medium viscosity, non promoted unsaturated polyester resin specially design for making putty.

II. PERFORMANCE

- Long stability.
- Good adhesion.
- Excellent sanding properties.
- Good flexibility.

III. SUGGESTED USES

• For the manufacture of polyputty for autobody repair.

IV. SPECIFICATION

Non-Volatile (105 °C, 3 hours)
 Viscosity at 25 °C, cPs
 63 - 66 %
 400 - 500

(Brookfield LVT, No.3/60 rpm)

• Acid Value : maximum 32 mg KOH/g

• Color : yellow - brownish

Appearance : clean/clear

• Gelling time at 25 °C, * : 13 - 18 minutes

V. STANDARD PACKING

220 kgs in metal drum.

VI. STORAGE

- Storage life decreases with increasing temperature.
- Avoid exposure to heat source such as direct sunlight or steam pipes.
- Keep containers sealed to prevent moisture pick up and monomer loss.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

Revised no

: 2

Revised date: August 10, 2009



TECHNICAL DATA SHEET

*) 1 % Co. Oct 8 %, 4 % MEKPO 50 %

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

| April 17, 2001

Revised no

: 2

Revised date: August 10, 2009